

PRODUCT DATA SHEET

ABSTRACT CONCRETE DYES™

BY HP SPARTACOTE®



PRODUCT DATA

Formulated exclusively for use with HP Spartacote® coatings and sealers, Abstract Concrete Dyes™ are available in an ultra low voc solution which is capable of being diluted in either water or acetone. Unlike dye powder concentrates, Abstract Dyes™ are ready for immediate use in a variety of decorative concrete applications. These products are intended to be used in Sparta-Stain™ and Sparta-Stain Pure™ decorative coating systems from HP Spartacote®. They can be applied directly to prepared concrete, polished concrete or polymer modified overlays. Abstract Dyes™ create exceptional translucent color effects that are similar to reactive concrete stains. Available in 15 different colors with unlimited versatility, Abstract Dyes™ offer a viable solution for an array of decorative concrete projects.

Features & Benefits

- ▶ Deeply penetrates and resides in the microscopic voids and substrate structure of properly prepared concrete and overlay surfaces.
- ▶ Abstract Concrete Dyes™ are a viable alternative to traditional reactive stains, for projects when a larger color palette or ease of installation is required.
- ▶ Abstract Concrete Dyes™ are also ideal for polished concrete due to depth of penetration.
- ▶ Abstract Concrete Dyes™ can be utilized in conjunction with all HP Spartacote® products as a coloration tool in the production of concrete flooring and pre-cast elements.
- ▶ Abstract Concrete Dyes™ are manufactured as a VOC compliant liquid concentrate. It is designed to be diluted with a non aromatic or aliphatic solvent like water or acetone.

For Professional Use Only

Thoroughly read all technical data sheets, application guidelines, warranty disclaimers and msds sheets prior to use. Application guides depending on the dye system employed are available at www.hpspartacote.com.

Packaging

5 oz and 25 oz liquid concentrate containers. Abstract Dye™ must be mixed with either water, acetone or alcohol prior to application.

Pre-Application

HP Spartacote, Inc. utilizes the International Concrete Repair Institute (ICRI) Concrete Surface Profile (CSP) standards for specifying finished surface roughness

prior to applying Abstract Concrete Dyes™. When applied direct to concrete, the concrete must be a minimum CSP 2 according to the ICRI CSP chart. Contact the ICRI at www.ICRI.org or HP Spartacote, Inc. for more information on these surface profiles.

The following liquids are recommended to use for diluting Abstract Concrete Dyes™:

- ▶ Acetone - Short dwell time, with consistent color. Will penetrate fairly dense concrete surfaces.
- ▶ Water - Long dwell time, with increased marbling. Surface needs to be porous.

Coverage Rates:

Coverage rates may vary greatly depending on substrate porosity, substrate color and dilution utilized to achieve desired final appearance. Material usage is approximately 400 square feet per gallon.

Mixing:

Mix the entire contents of the 5 oz. dye concentrate with one (1) gallon of the desired liquid diluent. Mix the entire contents of the 25 oz. dye concentrate with 5 gallons of the desired liquid. Drying times can be dramatically affected by temperature and humidity if diluted with water rather than acetone. Application must be made to concrete with a temperature higher than 50°F and maintained at this temperature or above for a minimum of 4 hours after application. Typical dry time is 30 seconds to 30 minutes at 70°F and 50% relative humidity. Dry times are also dependent upon the water or solvent carrier ratios.

Application:

Always complete a job site sample. Abstract Concrete Dye™ are best applied with an airless backpack pump-up sprayer or good quality solvent-resistant sprayer. Apply Abstract Concrete Dye™ in light spray applications. Once the subsequent dye application has dried, additional light applications of the same color or other colors can put down to build color depth or create marbling effects. If using recommended Sparta-Flex® sealers by HP Spartacote®, maintain a maximum 100-grit level profile to allow for optimal sealer adhesion and durability. For application to cementitious overlays and intermediary Sparta-Stain® systems, please reference the Sparta-Stain® application guides available at: www.hpspartacote.com.